



Stållina 6x12-7FC

Produktinformation



Konstruktion: 6x12-7FC (72-trådig)

Fyllnadsfaktor: 0.30

Art.nr	Lindiameter mm	Trådållfasthet N/mm ²	Ytbehandling	Rope lay.	Min brottkraft kN	Stålärea mm ²	Smörjning	Vikt kg/100m
101100304250270	3	1 770	Galvaniserad	sZ	3,33	2,09	Dry	2,1
101100404250270	4	1 770	Galvaniserad	sZ	5,92	3,71	Dry	3,7
101100504250270	5	1 770	Galvaniserad	sZ	9,25	5,8	Dry	5,8
101100604250270	6	1 770	Galvaniserad	sZ	13,3	8,35	Dry	8,3
101100704250270	7	1 770	Galvaniserad	sZ	18,1	11,4	Dry	11
101100804250270	8	1 770	Galvaniserad	sZ	23,7	14,8	Dry	15
101101004250270	10	1 770	Galvaniserad	sZ	37	23,2	Dry	23
101101204250270	12	1 770	Galvaniserad	sZ	53,3	33,4	Dry	33